



## Molded Grating Load Table

Concentrated Line Load Deflection														
Deflection in inches														
Span (in)	Depth (in)	Mesh (in)	Load (in pounds)								Max Recommended Load (psf)			Ultimate Capacity (psf)
			50	100	200	300	500	1000	2000	--	GP Resin	Poly Resin	VE Resin	
12	1	1x4	<0.01	0.01	0.02	0.02	0.04	0.08	--	1,180	1,180	2,310	5,350	
	1	1.5x1.5	<0.01	0.01	0.03	0.04	0.06	0.13	--	790	790	1,540	3,560	
	1.5	1.5x1.5	<0.01	<0.01	0.01	0.02	0.03	0.05	0.11	1,030	1,410	3,850	8,000	
18	1	1x4	0.01	0.02	0.05	0.07	0.12	0.23	--	780	780	1,540	3,560	
	1	1.5x1.5	0.02	0.04	0.08	0.12	0.20	0.41	--	520	520	1,020	2,370	
	1.5	1.5x1.5	0.01	0.02	0.03	0.05	0.08	0.15	0.30	880	940	2,560	5,330	
24	1	1x4	0.03	0.06	0.12	0.18	0.30	--	--	590	590	1,150	2,670	
	1	1.5x1.5	0.05	0.10	0.20	0.30	0.49	--	--	390	390	770	1,780	
	1.5	1.5x1.5	0.02	0.03	0.07	0.10	0.17	0.33	--	510	700	1,920	4,000	
30	1	1x4	0.05	0.11	0.22	0.32	--	--	--	470	470	920	2,140	
	1	1.5x1.5	0.09	0.18	0.35	--	--	--	--	310	310	610	1,420	
	1.5	1.5x1.5	0.03	0.06	0.12	0.18	0.29	--	--	410	560	1,540	3,200	
36	1	1x4	0.09	0.17	0.34	--	--	--	--	390	390	770	1,780	
	1	1.5x1.5	0.16	0.33	--	--	--	--	--	260	260	510	1,180	
	1.5	1.5x1.5	0.05	0.11	0.21	0.32	--	--	--	340	470	1,280	2,660	
42	1	1x4	0.15	0.30	--	--	--	--	--	330	330	660	1,520	
	1	1.5x1.5	0.23	0.45	--	--	--	--	--	220	220	440	1,010	
	1.5	1.5x1.5	0.08	0.16	0.32	0.47	--	--	--	290	400	1,100	2,280	
46	1	1x4	0.20	0.40	--	--	--	--	--	300	300	600	1,390	
	1	1.5x1.5	0.32	--	--	--	--	--	--	200	200	400	900	
48	1.5	1.5x1.5	0.11	0.23	0.45	--	--	--	--	250	350	960	2,000	
54	1.5	1.5x1.5	0.15	0.30	--	--	--	--	--	230	310	850	1,770	




## Molded Grating Load Table

Concentrated Point Load Deflection									
Span (in)	Depth (in)	Mesh (in)	Load (in pounds)						
			50	100	200	300	500	1000	2000
18	1	1x4	<0.01	0.01	0.02	0.03	0.06	0.11	0.22
	1	1.5x1.5	<0.01	0.01	0.03	0.04	0.07	0.14	0.27
	1.5	1.5x1.5	<0.01	<0.01	0.01	0.02	0.03	0.06	0.13
24	1	1x4	0.01	0.02	0.05	0.07	0.12	0.24	0.49
	1	1.5x1.5	0.01	0.03	0.05	0.08	0.13	0.26	---
	1.5	1.5x1.5	<0.01	0.01	0.02	0.03	0.06	0.12	0.23
30	1	1x4	0.02	0.05	0.09	0.14	0.23	0.45	---
	1	1.5x1.5	0.03	0.05	0.10	0.15	0.26	---	---
	1.5	1.5x1.5	0.01	0.02	0.04	0.06	0.10	0.20	---
36	1	1x4	0.04	0.07	0.14	0.21	0.35	---	---
	1	1.5x1.5	0.03	0.07	0.14	0.20	0.34	---	---
	1.5	1.5x1.5	0.02	0.03	0.06	0.09	0.15	0.30	---
42	1	1x4	0.05	0.11	0.21	0.32	---	---	---
	1	1.5x1.5	0.06	0.12	0.23	0.35	---	---	---
	1.5	1.5x1.5	0.02	0.04	0.09	0.13	0.22	0.44	---
46	1	1x4	0.07	0.13	0.26	0.39	---	---	---
	1	1.5x1.5	0.07	0.14	0.28	0.42	---	---	---
48	1.5	1.5x1.5	0.03	0.06	0.12	0.18	0.29	---	---
54	1.5	1.5x1.5	0.04	0.07	0.15	0.22	0.37	---	---
58	1.5	1.5x1.5	0.04	0.08	0.17	0.25	0.42	---	---




## Molded Grating Load Table

Uniform Load Deflection															
Deflection in inches															
Span (in)	Depth (in)	Mesh (in)	Load (in pounds)								Max Recommended Load (psf)			Ultimate Capacity (psf)	
			50	65	100	150	200	300	500	1000	GP Resin	Poly Resin	VE Resin		
12	1	1x4	<0.01	<0.01	<0.01	<0.01	<0.01	0.01	0.02	0.05	0.09	2,360	2,360	4,620	10,150
	1	1.5x1.5	<0.01	<0.01	<0.01	<0.01	0.01	0.02	0.04	0.08	0.16	1,580	1,580	3,080	6,770
	1.5	1.5x1.5	<0.01	<0.01	<0.01	<0.01	<0.01	0.01	0.02	0.04	0.07	2,060	2,830	7,700	10,420
18	1	1x4	0.01	0.01	0.02	0.03	0.04	0.07	0.11	0.22	0.44	1,050	1,050	2,050	4,750
	1	1.5x1.5	0.02	0.02	0.04	0.06	0.08	0.11	0.20	0.38	--	700	700	1,370	3,170
	1.5	1.5x1.5	<0.01	<0.01	0.01	0.02	0.03	0.04	0.07	0.14	0.28	910	1,250	3,420	6,940
24	1	1x4	0.04	0.05	0.07	0.11	0.15	0.22	0.37	--	--	590	590	1,150	2,670
	1	1.5x1.5	0.06	0.08	0.12	0.19	0.25	0.37	--	--	--	390	390	770	1,780
	1.5	1.5x1.5	0.02	0.03	0.04	0.06	0.06	0.12	0.21	0.42	--	510	700	1,920	4,000
30	1	1x4	0.08	0.11	0.17	0.26	0.34	--	--	--	--	370	370	740	1,710
	1	1.5x1.5	0.14	0.18	0.27	0.41	--	--	--	--	--	250	250	490	1,140
	1.5	1.5x1.5	0.05	0.06	0.09	0.14	0.18	0.27	0.46	--	--	330	450	1,230	2,560
36	1	1x4	0.16	0.21	0.32	0.49	--	--	--	--	--	260	260	510	1,180
	1	1.5x1.5	0.31	0.40	--	--	--	--	--	--	--	170	170	340	790
	1.5	1.5x1.5	0.10	0.13	0.20	0.30	0.40	--	--	--	--	230	310	850	1,770
42	1	1x4	0.33	0.43	--	--	--	--	--	--	--	190	190	370	870
	1	1.5x1.5	0.49	--	--	--	--	--	--	--	--	120	120	250	580
	1.5	1.5x1.5	0.17	0.22	0.34	--	--	--	--	--	--	160	230	620	1,300
46	1	1x4	0.48	--	--	--	--	--	--	--	--	160	160	310	720
48	1.5	1.5x1.5	0.28	0.37	--	--	--	--	--	--	--	120	170	480	1,000
54	1.5	1.5x1.5	0.42	--	--	--	--	--	--	--	--	100	140	380	790



## Pultruded Grating Load Table

Concentrated Line Load Deflection for I-Beam													
Deflection in inches													
Span (in)	Style	Depth (in)	Open Area	Load (in pounds)								Max Recommended Load (psf)	Ultimate Capacity (psf)
				50	100	200	300	500	1000	2000	---		
12	I-6010	1	60%	< 0.01	< 0.01	< 0.01	< 0.01	0.01	0.03	0.06	3,570	7,140	
	I-6015	1.5	60%	< 0.01	< 0.01	< 0.01	< 0.01	< 0.01	0.01	0.02	7,620	15,240	
18	I-6010	1	60%	< 0.01	0.01	0.02	0.03	0.04	0.09	0.17	3,390	6,780	
	I-6015	1.5	60%	< 0.01	< 0.01	< 0.01	0.01	0.02	0.03	0.06	7,370	14,740	
24	I-6010	1	60%	0.01	0.02	0.04	0.06	0.09	0.19	0.38	2,840	5,680	
	I-6015	1.5	60%	< 0.01	< 0.01	0.01	0.02	0.03	0.07	0.14	4,880	9,760	
30	I-6010	1	60%	0.02	0.03	0.07	0.10	0.17	0.35	---	2,300	4,600	
	I-6015	1.5	60%	< 0.01	0.01	0.03	0.04	0.06	0.13	0.26	4,500	9,000	
36	I-6010	1	60%	0.03	0.06	0.11	0.17	0.28	---	---	1,970	3,940	
	I-6015	1.5	60%	0.01	0.02	0.04	0.06	0.10	0.20	0.40	3,750	7,500	
42	I-6010	1	60%	0.04	0.08	0.17	0.25	0.42	---	---	1,670	3,340	
	I-6015	1.5	60%	0.02	0.03	0.06	0.10	0.16	0.32	---	3,220	6,440	
48	I-6010	1	60%	0.06	0.11	0.23	0.34	---	---	---	1,440	2,880	
	I-6015	1.5	60%	0.02	0.05	0.09	0.14	0.23	0.46	---	2,810	5,620	
54	I-6010	1	60%	0.09	0.18	0.36	---	---	---	---	1,280	2,560	
	I-6015	1.5	60%	0.03	0.07	0.14	0.21	0.35	---	---	2,500	5,000	
60	I-6010	1	60%	0.13	0.27	---	---	---	---	---	1,150	2,300	
	I-6015	1.5	60%	0.05	0.10	0.20	0.30	0.49	---	---	2,250	4,500	
72	I-6010	1	60%	0.26	---	---	---	---	---	---	960	1,920	
	I-6015	1.5	60%	0.09	0.18	0.36	---	---	---	---	1,880	3,760	



## Pultruded Grating Load Table

Uniform Load Deflection for I-Beam													
Deflection in inches													
Span (in)	Style	Depth (in)	Open Area	Load (in pounds)								Max Recommended Load (psf)	Ultimate Capacity (psf)
				50	100	200	300	500	1000	2000	---		
12	I-6010	1	60%	< 0.01	< 0.01	< 0.01	< 0.01	0.01	0.02	0.04	3,570	7,140	
	I-6015	1.5	60%	< 0.01	< 0.01	< 0.01	< 0.01	< 0.01	0.01	0.02	7,620	15,240	
18	I-6010	1	60%	< 0.01	0.01	0.02	0.02	0.04	0.08	0.16	2,260	4,520	
	I-6015	1.5	60%	< 0.01	< 0.01	< 0.01	0.01	0.02	0.03	0.06	4,910	9,820	
24	I-6010	1	60%	0.01	0.02	0.05	0.07	0.12	0.24	---	1,690	3,380	
	I-6015	1.5	60%	< 0.01	0.01	0.02	0.03	0.04	0.09	0.17	3,190	6,380	
30	I-6010	1	60%	0.03	0.05	0.11	0.16	0.27	---	---	1,370	2,740	
	I-6015	1.5	60%	0.01	0.02	0.04	0.06	0.10	0.20	0.41	2,950	5,900	
36	I-6010	1	60%	0.05	0.10	0.21	0.31	---	---	---	1,180	2,360	
	I-6015	1.5	60%	0.02	0.04	0.08	0.11	0.19	0.38	---	2,460	4,920	
42	I-6010	1	60%	0.09	0.19	0.37	---	---	---	---	950	1,900	
	I-6015	1.5	60%	0.04	0.07	0.14	0.21	0.35	---	---	1,840	3,680	
48	I-6010	1	60%	0.14	0.29	---	---	---	---	---	720	1,440	
	I-6015	1.5	60%	0.06	0.11	0.23	0.34	---	---	---	1,410	2,820	
54	I-6010	1	60%	0.25	---	---	---	---	---	---	570	1,140	
	I-6015	1.5	60%	0.10	0.19	0.39	---	---	---	---	1,110	2,220	
60	I-6010	1	60%	0.42	---	---	---	---	---	---	460	920	
	I-6015	1.5	60%	0.15	0.31	---	---	---	---	---	900	1,800	
72	I-6015	1.5	60%	0.34	---	---	---	---	---	---	630	1,260	